

textile specifications

	A		B						C	
STYLE	OPEN HOUSE 2334	PSEUDO 17300	LULLABY 34072	BON BON 34076	MARY GO ROUND 34079	EQUINOX 34074	WICKER 34075	HIGHBEAMS 9834	COBBLE 2563	LADDERS 2561
Contents	100% recycled polyester	100% polyester	100% recycled polyester	100% recycled polyester	100% recycled polyester	100% recycled polyester	100% recycled polyester	100% recycled polyester	100% recycled polyester	100% recycled polyester
Weight	12.4 ± 1.0 oz./lin.yd.	10.7 ± 1.0 oz./lin.yd.	12.0 ± 0.5 oz./lin.yd.	13.4 ± 0.5 oz./lin.yd.	10.5 ± 0.5 oz./lin.yd.	11.3 ± 0.5 oz./lin.yd.	13.3 ± 0.5 oz./lin.yd.	11.2 ± 0.5 oz./lin.yd.	9.2 ± 0.5 oz./lin.yd.	15.3 ± 1.0 oz./lin.yd.
Width	54" min. useable	54" min. useable	54" min. useable	54" min. useable	54" min. useable	54" min. useable	54" min. useable	54" min. useable	54" min. useable	54" min. useable
Repeat	none	none	1.2" vertical, 2.25" horizontal	5.0" vertical, 6.75" horizontal	3.78" vertical, 3.375" horizontal	4.5" vertical, 4.5" horizontal	.66" vertical, .9375" horizontal	none	3.7" vertical, 4.7" horizontal	none
Backing	none	none	none	none	none	none	none	none	none	none
Directional Fabric	no	yes	yes	yes	yes	yes	yes	yes	yes	yes
Treatment	none	stain resistant	BLOCKaide™	BLOCKaide™	BLOCKaide™	BLOCKaide™	BLOCKaide™	none	none	none
Cleaning Code	W-S	W-S	W-S	W-S	W-S	W-S	W-S	W-S	W-S	W-S
Cleaning Instructions	clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup	clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup	clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup	clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup	clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup	clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup	clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup	clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup	clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup	clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup

PERFORMANCE

Breaking Strength (ASTM D5034)	275 lbs. min. warp and fill	182 lbs. min. warp 184 lbs. min. fill	200 lbs. min. warp 300 lbs. min. fill	200 lbs. min. warp 275 lbs. min. fill	200 lbs. min. warp 250 lbs. min. fill	200 lbs. min. warp 300 lbs. min. fill	200 lbs. min. warp 275 lbs. min. fill	200 lbs. min. warp and fill	240 lbs. min. warp 130 lbs. min. fill	275 lbs. min. warp and fill
Tear (ASTM D2261)	35 lbs. min. warp and fill	13 lbs. min. warp 11 lbs. min. fill	25 lbs. min. warp 35 lbs. min. fill	25 lbs. min. warp 40 lbs. min. fill	25 lbs. min. warp and fill	20 lbs. min. warp 35 lbs. min. fill	35 lbs. min. warp 45 lbs. min. fill	10 lbs. min. warp and fill	20 lbs. min. warp and fill	20 lbs. min. warp and fill
Seam Slippage (ASTM D4034)	50 lbs. min. warp and fill	90 lbs. min. warp 97 lbs. min. fill	60 lbs. min. warp and fill	40 lbs. min. warp and fill	60 lbs. min. warp and fill	55 lbs. min. warp and fill	35 lbs. min. warp and fill	70 lbs. min. warp and fill	60 lbs. min. warp 40 lbs. min. fill	60 lbs. min. warp and fill
Pilling Resistance (ASTM D3511)	class 4 min.	class 4 min.	class 4 min.	class 4 min.	class 4 min.	class 4 min.	class 4 min.	class 4 min.	class 4 min.	class 4 min.
Colorfastness to Light (AATCC 16 Option 3)	40 hrs. min.	40 hrs. min.	40 hrs. min.	40 hrs. min.	40 hrs. min.	40 hrs. min.	40 hrs. min.	40 hrs. min.	40 hrs. min.	40 hrs. min.
Colorfastness to crocking (AATCC 8)	class 4 min. dry, class 3 min. wet	class 4 min. dry, class 3 min. wet	class 4 min. dry, class 3 min. wet	class 4 min. dry, class 3 min. wet	class 4 min. dry, class 3 min. wet	class 4 min. dry, class 3 min. wet	class 4 min. dry, class 3 min. wet	class 4 min. dry, class 3 min. wet	class 4 min. dry, class 3 min. wet	class 4 min. dry, class 3 min. wet
Colorfastness to water (AATCC 107)	class 3 min. for staining, class 4 min. for color change	class 3 min. for staining, class 4 min. for color change	class 3 min. for staining, class 4 min. for color change	class 3 min. for staining, class 4 min. for color change	class 3 min. for staining, class 4 min. for color change	class 3 min. for staining, class 4 min. for color change	class 3 min. for staining, class 4 min. for color change	class 3 min. for staining, class 4 min. for color change	class 3 min. for staining, class 4 min. for color change	class 3 min. for staining, class 4 min. for color change
Abrasion Resistance (ASTM D4157)	250,000 double rubs - cotton duck	30,000 double rubs - wire screen	30,000 double rubs - cotton duck	30,000 double rubs - cotton duck	30,000 double rubs - cotton duck	30,000 double rubs - cotton duck	30,000 double rubs - cotton duck	50,000 double rubs - cotton duck	30,000 double rubs - cotton duck	100,000 double rubs - cotton duck

FLAMMABILITY

State of CA. Tech. Bulletin, 117 SEC. E	passes	passes	passes	passes	passes	passes	passes	passes	passes	passes
UFAC	class 1	class 1	class 1	class 1	class 1	class 1	class 1	class 1	class 1	class 1
NFPA 260	class 1	class 1	class 1	class 1	class 1	class 1	class 1	class 1	class 1	class 1



NOTE: Colors may vary slightly between dye lots, application testing of all products is recommended.